

TECHNICAL DATA SHEET

RESIN K-4250

Short oil alkyd based on pentaerithritol and Dco oil modified with rosin

PRINCIPAL PROPERTIES

- High Gloss
- Excellent adhesion
- Very good flow
- Solubility in MTO

APPLICATIONS

It is used in second quality air drying synthetic enamels and primers as well as general purpose stoving enamels.

PRODUCT SPECIFICATION

PARAMETER	SPECIFICATION
Type of oil	Castor oil
Oil length	45
Acid value on solid	<25 mg KOH /gm
Viscosity 50% solid in MTO	100-120 seconds B-4 @30 C
Colour on gardener scale	8.0 Max.
Clarity	Clear
Non-volatile content	50+ ₋₂ %
Surface dry	3-4 Hours
Hard dry	12 Hours

